



THE LIME CENTRE

The Lime Centre Ltd, Hazeley Road, Morestead, Winchester, Hampshire SO21 1LZ
Tel: 01962 713636 | info@thelimecentre.co.uk | www.thelimecentre.co.uk

Product Name: Ultra

- Ultra is a thermally insulating lime basecoat for rendering and plastering.
- Lime Green Ultra is made with natural hydraulic lime and light weight mineral aggregates.
- Finished externally with a top coat of Lux available in a range of colours or internally with Solo lime plaster.
- Ideal for historic buildings.

Packaging

15 litre bags, 80no. per pallet.

For handling purposes assume 10kg per bag.

Coverage

One bag will cover:

1.5m² at 10mm

1m² at 15mm

0.6m² at 25mm

Surface Preparation

Remove dust, surface contaminants and loose or friable existing render/plaster. Where necessary consolidate or dub out any deep holes with Duro and key.

Ensure masonry is not waterproofed or painted, do not apply PVA. Dampen the surface with a mist spray in sufficient quantity to reduce excess suction.

Mixing/Water Addition

Add the whole bag of Ultra into a drum or forced action mixer, carefully avoiding creating excessive dust. Add 4-5 litres of clean water to each 15L sack. Mix for up to 10 minutes in a mixer, or use a mechanical whisk for 2-3 minutes, stand for 10 minutes, then mix once more before application. Do not add anything other than clean water.

Application

Applied in coats to a total depth of 30mm on to a prepared background.

Embedded fibre mesh is standard practice for rendering around windows and other areas of potential

stress or movement and in some cases the whole surface is meshed.

Fibre mesh (9mm x 10mm) is embedded into the first basecoat by applying in 2 passes with the mesh trowelled in between passes. Fibre mesh overlaps at no less than 100mm. The mesh can be doubled up at the stress points around windows and doors with diagonal pieces of at least 200mm x 400mm in size being trowelled with plaster against the surface before application of the basecoat

Each coat must be scratched to give a good mechanical key before further coats are applied. Dampen down the surface prior to coating. A second Ultra coat maybe applied after the previous has adequately cured, usually 2-4 days. Key the final coat of Ultra whilst still green with a nail or devil float before applying the finish coat of Lux render or Solo lime plaster.

Temperatures: above 5°C and below 30°C.

Reworking: avoid re-working.

Further coats: after 2 to 7 days, once the coat has stiffened/ hardened, but is still 'green'.

Curing

Prevent all coats from drying out too rapidly. Lightly spray each coat with water if it is hot or the product is drying out too quickly.

Protect from adverse conditions such as frost, rain, etc.

Adequate curing of a final decorative coat should be more stringent, ideally using a fully sheeted scaffold when outside.

Finish Coat

Finish externally with 4mm of Lux available in a range of colours or internally with 3mm of Solo lime plaster or Heritage Range Extra Fine Finish.




THE LIME CENTRE

The Lime Centre Ltd, Hazeley Road, Morestead, Winchester, Hampshire SO21 1LZ
Tel: 01962 713636 | info@thelimecentre.co.uk | www.thelimecentre.co.uk

Performance Data

Test	Result	Standard
Compressive strength @ 28 days N/mm ²	>1 (CSI)	EN1015
Compressive strength @ 90 days N/mm ²	>2	
Capillary water absorption kg/m.min ²	W1	EN1015
Bulk Density (Dry) grams	700	EN1015
Vapour Permeability	<15	EN1015
Thermal Conductivity w/m.K (Tab.)	0.18	En1745
Thermal Conductivity w/m.K (actual)	0.18	En 1745



Lime Green Products Ltd

Coates Kilns, Stretton Road, Much Wenlock, TF13 6DG

EN 998-1

Prescribed General Purpose (GP) Render and Plaster for internal and external use.

Typical U values

U Value w/ m²K

	35mm Standard Lime Plaster	35mm Ultra & 3mm Solo
215 Brick wall	1.73	1.10
330 Brick wall	1.28	0.90



THE LIME CENTRE

The Lime Centre Ltd, Hazeley Road, Morestead, Winchester, Hampshire SO21 1LZ
Tel: 01962 713636 | info@thelimecentre.co.uk | www.thelimecentre.co.uk

Hazard Statements:

- Causes skin irritation.
- Causes serious eye damage.
- May cause respiratory irritation.

Precautionary Statements:

- Keep out of reach of children.
- Wear protective gloves/protective clothing/eye protection/ face protection.
- In case of contact with eyes, rinse carefully with clean water for several minutes. In relevant cases, take out contact lenses if possible. Seek professional assistance for a Doctor (Hospital).
- If in contact with skin wash abundantly with soap and water.
- Avoid breathing dust/spray.
- If inhaled remove person to fresh air and keep at rest in a position comfortable for breathing.
- Dispose of contents via conventional waste management facilities. Before disposal NHL lime should be made inert by wetting to induce hardening and bags should be completely emptied

Control Measures:

- Corrosive to brass and aluminium.
- Keep away from strong oxidising agents.
- Prevent alkaline run off from entering storm drains.